

6165 W Detroit St. • Chandler AZ 85226  
 +1 (602) 276-0406 • +1 (800) 528-8242 • FAX +1 (480) 961-0513  
 www.crafco.com

**READ BEFORE USING THIS PRODUCT**

**GENERAL** Mastic One is a hot-applied, pourable, aggregate filled, black color, polymer modified asphalt pavement repair mastic. Mastic One complies with ASTM D8260 Type I. Mastic One is used for sealing, filling and repairing many distresses in both asphalt concrete and portland cement concrete pavements and bridge deck surfaces that are larger than those typically repaired by crack or joint sealing, but smaller than repairs requiring remove and replace patching procedures. Typical uses include sealing, filling and leveling of wide transverse or longitudinal cracks and joints, filling potholes and utility cuts, localized skin patch repairs, repairs prior to surface treatments, and leveling bridge approaches or faulted areas. When properly applied, Mastic One forms a well-bonded, flexible, durable, traffic resistant repair. To use, Mastic One is placed into an appropriate melter (Crafco Patcher units), mixed and heated until application temperature is reached, poured into the prepared repair area and then leveled. Mastic One is formulated to provide neat feathered edge installation. Mastic One is then ready for traffic when it has cooled and solidified. VOC = 0 g/l.

**PROPERTIES** Properties of the binder, aggregate and blended and heated Mastic One according to ASTM D8260 are as follows:

<u>Property</u>	<u>Requirement</u>
<b>POLYMER MODIFIED BINDER</b>	
Cone Penetration, 77°F (25°C) (ASTM D5329)	60 max
Cone Penetration, 122°F (50°C) (ASTM D5329)	120 max
Softening Point, (ASTM D36)	200°F (93°C) min
Flexibility, 1" (25.4 mm), 180°, 10 sec) (ASTM D3111 modified)	Pass at 32°F (0°C)
<b>AGGREGATE</b>	
Abrasion Resistance (ASTM C131)	35% max
<b>BLENDED PRODUCT</b>	
Flexibility, 32°F (0°C) (ASTM D5329)	Pass
Adhesion, 77°F (25°C) (ASTM D5329)	25 PSI (172 KPA) min
Specific Gravity	1.7 -2.0
Minimum Application Temperature	375°F (190°C) *
Maximum Application Temperature	400°F (204°C)

<u>Test</u>	<u>ASTM D8260 Type I Specification Limits</u>
Mastic Resilience (ASTM (8260)	50% minimum
Effects of Rapid Deformation (ASTM D2794) (-7°C)	3 passing specimens no chipping, cracking or separation 8 N-m
Crack Bridging (ASTM C1305 modified) (-7°C)	Pass 3 cycles
Mastic Stability (ASTM D8260) (70°C)	40.0 mm maximum

\*Refer to installation instructions if working on sloped pavements or repairing larger defects

**INSTALLATION** The density of Mastic One is 116 pcf (+/- 3%) and the weight per gallon is 15.5 lbs./gal (1.86 kg/l) at 60°F (15.5°C). Prior to use, the user must read and follow Installation Instructions for Mastic One to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are available at www.crafco.com and provided with each pallet of Mastic One.

**PACKAGING** Mastic One is supplied in either cardboard boxes, or in meltable, boxless PLEXI-melt packaging. Each package contains premeasured polymer modified binder and aggregate. Both package types are labeled in accordance with OSHA, GHS, and specification requirements; are sold by net weight; are interlock stacked on 48 x 40 in. (122 x102 cm) 4-way pallets; can be stored outside; and are covered with a weather resistant pallet cover and 2 layers of UV protected stretch wrap.

- o **BOX** packaging consists of cardboard boxes containing approximately 40 lb. (18.1 kg) of product with 60 boxes per pallet, weighing approximately 2400 lb. (1088 kg). Boxes contain a quick melting release film for easy removal and are taped closed, without any staples.
- o **PLEXI-melt** packaging consists of 30 lb. (13.6 kg) blocks of product with 70 packages per pallet, weighing 2100 lb. (952 kg). To use, the pallet wrap is removed, and individual blocks are placed in the melter. There are no cardboard boxes or other cardboard components to open, empty, handle, or dispose of. PLEXI-melt packaging quickly melts into the product without affecting specification conformance.

**WARRANTY** CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafco shall not be responsible for improperly applied or misused products. Remedies against Crafco, Inc., as agreed to by Crafco, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafco, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafco, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafco recommendations for product installation.**